



CLIENT:	Greely Sand & Gravel	DESCRIPTION:	Sand	FILE NO.:	PM0754
CONTRACT NO.:	-	SPECIFICATION:	<b>Mantle Sand (Eljen)</b>	LAB NO.:	04990
PROJECT:	Laboratory Testing	INTENDED USE:	-	DATE REC'D:	1-Oct-18
		PIT OR QUARRY:	Pit	DATE TESTED:	2-Oct-18
DATE SAMPLED:	01-Oct-18	SOURCE LOCATION:	Spratt	DATE REP'D:	4-Oct-18
SAMPLED BY:	Client	SAMPLE LOCATION:	Stockpile	TESTED BY:	D.B/E.B

WEIGHT BEFORE WASH			A+B	301.7
WEIGHT AFTER WASH	A	B	A+B	298.6

SIEVE SIZE (mm)	WEIGHT RETAINED	PERCENT RETAINED	PERCENT PASSING	LOWER SPEC	UPPER SPEC	REMARK
150						
106						
75						
63						
53						
37.5						
26.5						
19						
16						
13.2						
9.5	0.0	0.0	100.0	100.0	100.0	
6.7	5.1	1.7	98.3			
4.75	11.8	3.9	96.1	95.0	100.0	
2.36	42.1	14.0	86.0	80.0	100.0	
1.18	82.5	27.3	72.7	50.0	85.0	
0.6	136.0	45.1	54.9	25.0	60.0	
0.3	218.0	72.3	27.7	5.0	30.0	
0.15	282.8	93.7	6.3	0.0	10.0	
0.075	297.9	98.7	1.3	0.0	5.0	
PAN	298.6					

SIEVE CHECK FINE	0.00	0.3% max.	REFERENCE MATERIAL
------------------	------	-----------	--------------------

OTHER TESTS	RESULT	LAB NO.	RESULT

REVIEWED BY:	Curtis Beadow	Joe Forsyth, P. Eng.
		