

patersongroup consulting engineers				SIEVE ANALYSIS ASTM C136	
CLIENT:	Greely Sand & Gravel	DESCRIPTION:	Sand	FILE NO:	PM0754
CONTRACT NO.:	-	SPECIFICATION:	Mantle Sand (Eljen)	LAB NO:	07244
PROJECT:	Laboratory Testing	INTENDED USE:	-	DATE RECEIVED:	3-May-19
		PIT OR QUARRY:	Pit	DATE TESTED:	6-May-19
DATE SAMPLED:	-	SOURCE LOCATION:	Spratt Rd.	DATE REPORTED:	8-May-19
SAMPLED BY:	-	SAMPLE LOCATION:	-	TESTED BY:	N.V/D.K

Silt and Clay		Sand			Gravel		Cobble
		Fine	Medium	Coarse	Fine	Coarse	

Identification	Soil Classification					MC(%)	LL	PL	PI	Cc	Cu
	D100	D60	D30	D10	Gravel (%)	Sand (%)		Silt (%)		Clay (%)	
	6.8	0.59	0.31	0.17	2.7	95.4		1.9		0.96	3.5

Comments: The sample is representative of a Poorly graded fine to coarse sand with trace gravel and fines (SP) with an **Estimated T Time = 6 to 8 min/cm**. The percolation rate provided above is based on the gradation of the test sample submitted, and as such, is approximate only. The values chosen for design should take into account the expected density in the field. This material is acceptable for placement as Eljen Specified GFS Sand.

	Curtis Beadow	Joe Forsyth, P. Eng.
REVIEWED BY:		

patersongroup consulting engineers						SIEVE ANALYSIS ASTM C136	
CLIENT: Greely Sand & Gravel		DESCRIPTION: Sand		FILE NO.: PM0754			
CONTRACT NO.: -		SPECIFICATION: Mantle Sand (Eljen)		LAB NO.: 07244			
PROJECT: Laboratory Testing		INTENDED USE: -		DATE REC'D: 3-May-19			
		PIT OR QUARRY: Pit		DATE TESTED: 6-May-19			
DATE SAMPLED: -		SOURCE LOCATION: Spratt Rd.		DATE REP'D: 8-May-19			
SAMPLED BY: -		SAMPLE LOCATION: -		TESTED BY: N.V/D.K			
WEIGHT BEFORE WASH				303.3			
WEIGHT AFTER WASH				299.6			
SIEVE SIZE (mm)	WEIGHT RETAINED	PERCENT RETAINED	PERCENT PASSING	LOWER SPEC	UPPER SPEC	REMARK	
150							
106							
75							
63							
53							
37.5							
26.5							
19							
16							
13.2							
9.5				100.0	100.0		
6.7	0.0	0.0	100.0				
4.75	8.2	2.7	97.3	95.0	100.0		
2.36	33.6	11.1	88.9	80.0	100.0		
1.18	69.3	22.8	77.2	50.0	85.0		
0.6	121.2	40.0	60.0	25.0	60.0		
0.3	215.7	71.1	28.9	5.0	30.0		
0.15	282.1	93.0	7.0	0.0	10.0		
0.075	297.6	98.1	1.9	0.0	5.0		
PAN	299.0						
SIEVE CHECK FINE		0.20	0.3% max.			REFERENCE MATERIAL	
OTHER TESTS					RESULT	LAB NO.	RESULT
REVIEWED BY:	Curtis Beadow			Joe Forsyth, P. Eng.			
							