


CLIENT	Greely Sand & Gravel	DESCRIPTION:	Stone	FILE NO:	PM0754
CONTRACT NUMBER	•	SPECIFICATION:	Playground Stone	LAB NO:	1603
PROJECT	Laboratory Testing	INTENDED USE:	Misc.	DATE RECEIVED:	28-Jun-18
		PIT OR QUARRY:	Pit	DATE TESTED:	29-Jun-18
DATE SAMPLED	28-Jun-18	SOURCE LOCATION:	-	DATE REPORTED:	4-Jul-18
CAMPLED DV	0!:+	CAMPLELOCATION	0: 1 "	TEOTED DV	ED / DI/



consulting e	ngroup engineers					SIEVE AN ASTM (
CLIENT:	Greely Sa	nd & Gravel	DESCRIPTION:	St	one	FILE NO.:	PM0754
CONTRACT NO.:		-	SPECIFICATION:	Playgrou	und Stone	LAB NO.:	1603
PROJECT:	I aborato	ory Testina	INTENDED USE:	М	isc.	DATE REC'D:	28-Jun-18
PROJECT: Laboratory Testing		PIT OR QUARRY: Pit		DATE TESTED:	29-Jun-18		
DATE SAMPLED: 28-Jun-18		SOURCE LOCATION: -		DATE REP'D:	4-Jul-18		
SAMPLED BY:		lient	SAMPLE LOCATION		Stockpile	TESTED BY:	EB / DK
WEIGHT BEFORE				A+B	5662		
WEIGHT AFTER V	WASH	А	В	A+B			
SIEVE SIZE (mm)	WEIGHT RETAINED	PERCENT RETAINED	PERCENT PASSING	LOWER SPEC	UPPER SPEC	REMA	.RK
150							
106							
75							
63							
53							
37.5							
26.5							
19							
16	0.0	0.0	100.0				
13.2	0.0	0.0	100.0				
9.5	1213.6	21.4	78.6				
6.7	3759.1	66.4	33.6				
4.75	5423.1	95.8	4.2				
PAN	238.9	2.22			1		
SIEVE CHECK CC		0.00			0.3% max.		
WEIGHT FINE SIE	•)	251.5				
NIEGHT FINE SIE	WEIGHT	PERCENT RETAINED	PERCENT PASSING	PERCENT PASSING COMBINED	196.3 LOWER SPEC	UPPER SPEC	REMARK
		69.8	30.2	1.3			
2.36	175.5					+	
2.36	175.5 179.2			1.2			
2.36 1.18 0.6	175.5 179.2 180.6	71.3 71.8	28.7 28.2	1.2 1.2			
1.18	179.2	71.3	28.7				
1.18 0.6 0.3	179.2 180.6 183.1	71.3 71.8	28.7 28.2 27.2	1.2 1.1			
1.18 0.6 0.3 0.15	179.2 180.6 183.1 187.1	71.3 71.8 72.8 74.4	28.7 28.2 27.2 25.6	1.2 1.1 1.1			
1.18 0.6 0.3	179.2 180.6 183.1	71.3 71.8 72.8	28.7 28.2 27.2	1.2 1.1			
1.18 0.6 0.3 0.15 0.075	179.2 180.6 183.1 187.1 193.6 196.3	71.3 71.8 72.8 74.4	28.7 28.2 27.2 25.6	1.2 1.1 1.1		REFERENCE	MATERIAL

REVIEWED BY:		APPROVED BY:	0		
	Curtis Beadow		Joe Forsyth, P.Eng		