


CLIENT:	Greely Sand & Gravel	DESCRIPTION:	Sand	FILE NO:	PM0754
CONTRACT NO.:	-	SPECIFICATION:	Hydro Sand	LAB NO:	15399
PROJECT:	Laboratory Testing	INTENDED USE:	-	DATE RECEIVED:	5-May-20
		PIT OR QUARRY:	Pit	DATE TESTED:	7-May-20
DATE SAMPLED:	5-May-20	SOURCE LOCATION:	Pyper	DATE REPORTED:	8-May-20
SAMPLED BY:	Client	SAMPLE LOCATION:	-	TESTED BY:	DK



Silt and Clay	Sand			Gravel		Cobble
	Fine	Medium	Coarse	Fine	Coarse	

Comments:

This Sample Conforms to the Hydro Sand Grading Envelope

REVIEWED BY:	Curtis Beadow	Joe Fosyth, P. Eng.
	<i>Curtis Beadow</i>	<i>Joe Fosyth</i>

CLIENT: Greely Sand & Gravel	DESCRIPTION: Sand	FILE NO.: PM0754
CONTRACT NO.: -	SPECIFICATION: Hydro Sand	LAB NO.: 15399
PROJECT: Laboratory Testing	INTENDED USE: -	DATE REC'D: 5-May-20
	PIT OR QUARRY: Pit	DATE TESTED: 7-May-20
DATE SAMPLED: 5-May-20	SOURCE LOCATION: Pyper	DATE REP'D: 8-May-20
SAMPLED BY: Client	SAMPLE LOCATION: -	TESTED BY: DK

WEIGHT BEFORE WASH	334.0
WEIGHT AFTER WASH	319.1

SIEVE SIZE (mm)	WEIGHT RETAINED	PERCENT RETAINED	PERCENT PASSING	LOWER SPEC	UPPER SPEC	REMARK
150						
106						
75						
63						
53						
37.5						
26.5						
19						
16						
13.2						
9.5						
6.7				100.0	100.0	
4.75	0.0	0.0	100.0	100.0	100.0	
2.36	3.2	1.0	99.0	95.0	100.0	
1.18	16.0	4.8	95.2	90.0	100.0	
0.6	36.6	11.0	89.0	85.0	100.0	
0.3	128.4	38.4	61.6	45.0	85.0	
0.15	253.8	76.0	24.0	15.0	40.0	
0.075	310.8	93.1	6.9	0.0	7.0	
PAN	318.4					

SIEVE CHECK FINE	0.22	0.3% max.	REFERENCE MATERIAL
------------------	------	-----------	---------------------------

OTHER TESTS	RESULT	LAB NO.	RESULT

REVIEWED BY:	Curtis Beadow	Joe Forsyth, P. Eng.
	