

<b>patersongroup</b> consulting engineers				<b>SIEVE ANALYSIS</b> ASTM C136	
CLIENT:	Greely Sand & Gravel	DESCRIPTION:	Sand	FILE NO:	PM0754
CONTRACT NO.:	-	SPECIFICATION:	<b>Mantle Sand (Eljen)</b>	LAB NO:	15604
PROJECT:	Laboratory Testing	INTENDED USE:	-	DATE RECEIVED:	12-May-20
		PIT OR QUARRY:	Pit	DATE TESTED:	13-May-20
DATE SAMPLED:	12-May-20	SOURCE LOCATION:	Spratt Rd.	DATE REPORTED:	14-May-20
SAMPLED BY:	Client	SAMPLE LOCATION:	Stockpile	TESTED BY:	DK

  

Silt and Clay		Sand			Gravel		Cobble
		Fine	Medium	Coarse	Fine	Coarse	

Identification	Soil Classification					MC(%)	LL	PL	PI	Cc	Cu
	D100	D60	D30	D10	Gravel (%)	Sand (%)		Silt (%)		Clay (%)	
	4.75	0.55	0.25	0.17	4.3	94.1		1.6		0.67	3.2

**Comments:**

The sample is representative of a Poorly graded fine sand with trace fines and gravel (SP) with an Estimated T Time = **6 to 8 min/cm**. The percolation rate provided above is based on the gradation of the test sample submitted, and as such, is approximate only. The values chosen for design should take into account the expected density in the field. This material meets the grading requirements of Eljen Specified GFS Sand.

	<b>Curtis Beadow</b> 	<b>Joe Forsyth, P. Eng.</b> 
<b>REVIEWED BY:</b>		

patersongroup consulting engineers						SIEVE ANALYSIS ASTM C136	
CLIENT: Greely Sand & Gravel			DESCRIPTION: Sand			FILE NO.: PM0754	
CONTRACT NO.: -			SPECIFICATION: Mantle Sand (Eljen)			LAB NO.: 15604	
PROJECT: Laboratory Testing			INTENDED USE: -			DATE REC'D: 12-May-20	
			PIT OR QUARRY: Pit			DATE TESTED: 13-May-20	
DATE SAMPLED: 12-May-20			SOURCE LOCATION: Spratt Rd.			DATE REP'D: 14-May-20	
SAMPLED BY: Client			SAMPLE LOCATION: Stockpile			TESTED BY: DK	
WEIGHT BEFORE WASH						410.5	
WEIGHT AFTER WASH						406.5	
SIEVE SIZE (mm)	WEIGHT RETAINED	PERCENT RETAINED	PERCENT PASSING	LOWER SPEC	UPPER SPEC		
150							
106							
75							
63							
53							
37.5							
26.5							
19							
16							
13.2							
9.5	0.0	0.0	100.0	100.0	100.0		
6.7	5.5	1.3	98.7				
4.75	17.6	4.3	95.7	95.0	100.0		
2.36	64.4	15.7	84.3	80.0	100.0		
1.18	132.6	32.3	67.7	50.0	85.0		
0.6	180.5	44.0	56.0	25.0	60.0		
0.3	289.7	70.6	29.4	5.0	30.0		
0.15	392.8	95.7	4.3	0.0	10.0		
0.075	404.1	98.4	1.6	0.0	5.0		
PAN	405.5						
SIEVE CHECK FINE		0.25	0.3% max.			REFERENCE MATERIAL	
OTHER TESTS					RESULT	LAB NO.	RESULT
REVIEWED BY:	Curtis Beadow			Joe Forsyth, P. Eng.			
							