




**SIEVE ANALYSIS
ASTM C136**

CLIENT:	Greely Sand & Gravel	DESCRIPTION:	Fine Aggregate	FILE NO:	PM0754
CONTRACT NO.:	-	SPECIFICATION:	Decomposed Granite	LAB NO:	59354
PROJECT:	Laboratory Testing	INTENDED USE:	Misc.	DATE RECEIVED:	1-May-25
		PIT OR QUARRY:	Pit	DATE TESTED:	2-May-25
DATE SAMPLED:	30-Apr-25	SOURCE LOCATION:	Spratt	DATE REPORTED:	6-May-25
SAMPLED BY:	Client	SAMPLE LOCATION:	Stockpile	TESTED BY:	C.P



	Silt and Clay			Sand			Gravel			Cobble		
				Fine	Medium	Coarse	Fine		Coarse			
Identification	Soil Classification						MC(%)	LL	PL	PI	Cc	Cu
											0.81	31.8
	D100	D60	D30	D10	Gravel (%)		Sand (%)		Silt (%)		Clay (%)	
	6.7	1.75	0.28	0.055	4.7		81.5		13.8			
Comments:												
REVIEWED BY:	Curtis Beadow						Joe Fosyth, P. Eng.					
												

CLIENT: Greely Sand & Gravel		DESCRIPTION: Fine Aggregate		FILE NO.: PM0754		
CONTRACT NO.: -		SPECIFICATION: Decomposed Granite		LAB NO.: 59354		
PROJECT: Laboratory Testing		INTENDED USE: Misc.		DATE REC'D: 1-May-25		
		PIT OR QUARRY: Pit		DATE TESTED: 2-May-25		
DATE SAMPLED: 30-Apr-25		SOURCE LOCATION: Spratt		DATE REP'D: 6-May-25		
SAMPLED BY: Client		SAMPLE LOCATION: Stockpile		TESTED BY: C.P		
WEIGHT BEFORE WASH				523.7		
WEIGHT AFTER WASH				466.6		
SIEVE SIZE (mm)	WEIGHT RETAINED	PERCENT RETAINED	PERCENT PASSING	LOWER SPEC	UPPER SPEC	REMARK
150						
106						
75						
63						
53						
37.5						
26.5						
19						
16						
13.2						
9.5						
6.7	0.0	0.0	100.0			
4.75	24.7	4.7	95.3			
2.36	161.0	30.7	69.3			
1.18	256.3	48.9	51.1			
0.6	309.9	59.2	40.8			
0.3	359.5	68.6	31.4			
0.15	411.5	78.6	21.4			
0.075	451.3	86.2	13.8			
PAN	466.4					
SIEVE CHECK FINE		0.04	0.3% max.		REFERENCE MATERIAL	
OTHER TESTS				RESULT	LAB NO.	RESULT
REVIEWED BY:	Curtis Beadow			Joe Forsyth, P. Eng.		
	