


CLIENT:	Greely Sand & Gravel	DESCRIPTION:	Sand	FILE NO:	PM0754
CONTRACT NO.:	-	SPECIFICATION:	Eljen Sand	LAB NO:	59369
PROJECT:	Laboratory Testing	INTENDED USE:	Eljen Specified	DATE RECEIVED:	1-May-25
		PIT OR QUARRY:	Pit	DATE TESTED:	2-May-25
DATE SAMPLED:	30-Apr-25	SOURCE LOCATION:	Spratt	DATE REPORTED:	6-May-25
SAMPLED BY:	Client	SAMPLE LOCATION:	Stockpile	TESTED BY:	C.P





Silt and Clay	Sand			Gravel		Cobble
	Fine	Medium	Coarse	Fine	Coarse	

Identification	Soil Classification					MC(%)	LL	PL	PI	Cc	Cu
	D100	D60	D30	D10	Gravel (%)	Sand (%)		Silt (%)		Clay (%)	
	4.75	0.96	0.38	0.195	0.0	97.2		2.8			

**Comments:**

The sample is representative of a Poorly graded fine sand with trace fines and gravel (SP) with an Estimated T Time = 6 to 8 min/cm. The percolation rate provided above is based on the gradation of the test sample submitted, and as such, is approximate only. The values chosen for design should take into account the expected density in the field. This material meets the grading requirements of Eljen Specified GFS Sand.

REVIEWED BY:	Curtis Beadow					Joe Forsyth, P. Eng.					
											

CLIENT: Greely Sand & Gravel		DESCRIPTION: Sand		FILE NO.: PM0754		
CONTRACT NO.: -		SPECIFICATION: <b>Eljen Sand</b>		LAB NO.: 59369		
PROJECT: Laboratory Testing		INTENDED USE: Eljen Specified		DATE REC'D: 1-May-25		
		PIT OR QUARRY: Pit		DATE TESTED: 2-May-25		
DATE SAMPLED: 30-Apr-25		SOURCE LOCATION: Spratt		DATE REP'D: 6-May-25		
SAMPLED BY: Client		SAMPLE LOCATION: Stockpile		TESTED BY: C.P		
WEIGHT BEFORE WASH					574.1	
WEIGHT AFTER WASH					562.0	
SIEVE SIZE (mm)	WEIGHT RETAINED	PERCENT RETAINED	PERCENT PASSING	LOWER SPEC	UPPER SPEC	REMARK
150						
106						
75						
63						
53						
37.5						
26.5						
19						
16						
13.2						
9.5				100.0	100.0	
6.7						
4.75	<b>0.0</b>	0.0	<b>100.0</b>	95.0	100.0	
2.36	<b>81.3</b>	14.2	<b>85.8</b>	80.0	100.0	
1.18	<b>197.0</b>	34.3	<b>65.7</b>	50.0	85.0	
0.6	<b>305.9</b>	53.3	<b>46.7</b>	25.0	60.0	
0.3	<b>444.6</b>	77.4	<b>22.6</b>	5.0	30.0	
0.15	<b>543.0</b>	94.6	<b>5.4</b>	0.0	10.0	
0.075	<b>558.0</b>	97.2	<b>2.8</b>	0.0	5.0	
PAN	<b>561.5</b>					
SIEVE CHECK FINE		0.09	0.3% max.			<b>REFERENCE MATERIAL</b>
<b>OTHER TESTS</b>					<b>RESULT</b>	<b>LAB NO.</b>
<b>REVIEWED BY:</b>	<b>Curtis Beadow</b>			<b>Joe Forsyth, P. Eng.</b>		
	